



IWEISS

815 FAIRVIEW AVE #10
FAIRVIEW, NJ 07022
201-402-6500

KM Fabrics, Inc.

FABRIC SPECIFICATIONS

Pattern Name	<u>Charisma</u>	Pattern Number	<u>624</u>
Weight/Linear Yard	<u>24.1 oz./lin yard</u>	Ground Yarn & Count	<u>2/150/64 IFR Poly</u>
Pile Yarn & Count	<u>2/150/128 IFR Poly</u>	Ground Weight	<u>0.367</u>
Pile Weight	<u>0.767</u>	Ground Weight/ % of Total	<u>49%</u>
Pile Weight/ % of Total	<u>51%</u>	Ground Ends/Inch.	<u>48</u>
Pile Ends/Inch.	<u>51</u>	Filling Yarn & Count	<u>2/150/128 IFR poly</u>
Pile Tufts/Sq. Inch.	<u>1173</u>	Filling Weight	<u>0.367</u>
Pile Height/1000"	<u>120</u>	Filling Picks/Inch	<u>46</u>

PERFORMANCE

This Fabric Meets or Exceeds The Listed Standard Requirements

<u>Test</u>	<u>Standard Requirements</u>	<u>Test Method</u>
Abrasion (Heavy Duty)	15,000 double rubs ANSI/ASTM-D-3597-77	ASTM-D-1175-71-24 Wyzenbeek Test
Tensil Strength:		
Warp:	50 Lbs. Min.	ASTM-D-1682
Filling:	50 Lbs. Min. ANSI/ASTM-D-3597-77	
Tear Strength:	6 Lbs. Min. 6 Lbs. Min. ANSI/ASTM-D-3597-77	ASTM-D-2262
Crocking:	Class 4 Dry Min. Class 3 Med. Min. ANSI/ASTM-D-3597-77	AATCC-8-1974
Light Fastness:	Fading 60 Hours	AATCC-16A-1974

FLAMMABILITY

Manufactured To Meet The Following Requirements

MVS 302
BIFMA F-1-1978
SC-191-53 Class1 California
UFAC Class 1
NFPA 701